












# Würth FUGEGUIDE

PRODUKT	TEKNISKE DATA									TRE		METALL				MINERALISKE MATERIALER					PLAST					FARGER								
	UV-bestendig	Overmalbar *	Bearbeidings tid i min.	Herdetid mm/døgn	Elastisitet %	Temperaturbestandig etter utharding	Slipbarhet	Shore A	Fuktig underlag	Treverk	Teak	Zink/forsinkede overflater	Jern/stål	Aluminium	Rustfritt/Syrefast	Gips	Betong	Porebetong/Leca	Glass	Naturstein	Tegl	Hard PVC	Myk PVC	Polykarbonat	Glassfiberarmert polyester	Myk Termoplast PP PE	Astfalt/tjere/bitumen	Isopor	Transparent	Hvit	Grå	Lys grå	Sort	Øvrige farger tilgjengelig
 <b>Sanitær-silikon</b>	++	-	10	3	25	150	-	25	-	P	-	-	-	+	P	P	P	++	-	P	P	-	-	-	-	-	-	+	+	+	+	+	+	+
 <b>Bygg Silikon</b>	++	-	10-25	2	25	120	-	17	-	+	-	+	+	+	P	++	P	++	-	P	+	-	+	-	-	-	+	+	+	+	+	+	+	+
 <b>Akryl</b>	+	+	15	1	10	80	0	30	-	+	-	-	-	-	P	+	P	-	-	+	+	-	-	-	-	-	+	-	+	+	-	-	-	-
 <b>Tak-Tett</b>	++	+	15	1-2	25	100	-	25	++	+	-	+	+	+	+	+	+	+	-	+	+	-	-	-	-	++	-	+	+	+	-	+	-	-
 <b>Kleb og Tett</b>	0	++	50	4	10	90	+	40	-	P	P	P	P	P	P	P	P	+	-	P	P	-	-	-	-	-	-	+	+	+	-	+	+	+
 <b>Kleb og Tett Hurtigherdende</b>	0	++	30	6	10	80	+	35	-	P	-	P	P	P	P	P	P	+	-	P	P	-	-	-	-	-	-	+	+	+	-	+	-	-
 <b>Fugemasse PU</b>	0	+	120	1	20	70	0	25	-	P	P	P	P	P	P	P	P	+	-	+	P	-	-	-	-	-	-	+	+	+	-	+	+	+
 <b>MS-polymer 15 LM</b>	+	+	10	2	25	80	0	20	-	++	+	+	++	+	+	++	+	++	+	+	+	+	+	+	+	+	+	-	+	+	-	-	-	-
 <b>Klebmasse MS</b>	+	++	15	3	10	80	+	60	0	+	+	+	++	+	+	+	++	+	+	+	+	+	+	+	+	+	+	+	+	+	-	+	-	-
 <b>Brannsikker, elastisk fugemasse</b>	++	-	10	4	25	120	-	20	-	+	-	+	+	+	P	P	P	+	-	P	P	-	-	-	-	-	+	-	+	+	-	-	-	-
 <b>Brannhemmende akryl</b>	+	+	25	1	10	80	0	30	-	+	-	-	-	-	+	+	+	-	-	+	+	-	-	-	-	-	+	-	+	-	-	-	-	-

\* egne forsøk anbefales    P egnet primer    ++ meget godt egnet    + godt egnet    0 mindre egnet    - anbefales ikke

